

# **MAK ENGOL J**

## **Description**

MAK ENGOL J oils are compounded with fatty oils to provide good wettability.

## **Application**

These are recommended for lubrication in gear boxes, where high viscosity and compounded type of oils are required. These oils are also suitable for lubrication of worm gears where Sulphur / Phosphorus type EP additives are not recommended.

#### **Benefits**

- Provides excellent oiliness
- Possesses excellent film strength properties

#### **PERFORMANCE LEVEL**

• IS 1589: 1994 Type 2 [Reaffirmed March, 2001]

IPSS: 1-09-010

Our grades meet above specifications for the respective viscosity grades.



## **Storage and Handling**

| Characteristics                                       | IS 1448 | MAK ENGOL J            |                        |                        |                        |                         |                        |
|---|---------|------------------------|------------------------|------------------------|------------------------|-------------------------|------------------------|
|   |         | 460                    | 800                    | 1000                   | 1500                   | 521                     | 680                    |
| Appearance  |         | Dark<br>brown<br>fluid | Dark<br>brown<br>fluid | Dark<br>brown<br>fluid | Dark<br>brown<br>fluid | Dark<br>brow<br>n fluid | Dark<br>brown<br>fluid |
| Density at 15° C                                      | P:16    | 0.905                  | 0.9320                 | 0.9660                 | 0.9860                 | 0.913                   | 0.9202                 |
| K.V at 40° C, cSt                                     | P:25    | 460.5                  | 800.4                  | 1000.9                 | 1500.3                 | 521.4                   | 680.7                  |
| Viscosity Index                                       | P:56    | 95                     | 90                     | 90                     | 90                     | 92                      | 91                     |
| Pour Point, °C  | P:10    | -6                     | -3                     | -3                     | -3                     | -6                      | -6                     |
| Flash Point,<br>(COC), °C                             | P:69    | 256                    | 282                    | 286                    | 296                    | 262                     | 278                    |
| Copper Strip<br>Corrosion Test at<br>100°C for 3 hrs. | P:15    | la                     | 1a                     | 1a                     | la                     | 1a                      | 1a                     |

All the mentioned values are typical which may vary from batch to batch

# **Storage and Handling**

- Indoor Storage is always preferable
- Closed Barrels should be kept horizontally with bung position at 3'0Clock 9 'O Clock position
- Barrels should be kept away from dusty or heated areas as much as possible

# **Health & Safety**

This grade is not hazardous under normal conditions of use. For further guidance appropriate Material Safety Data Sheet may be referred.

#### Advice

For any further advice on applications or otherwise please contact the nearest Bharat Petroleum Territory Office or Technical Services Department at the address given below.

#### Bharat Petroleum Corporation Ltd.

Bharat Bhavan – II, First Floor, 4 & 6, Currimbhoy Road, Ballard Estate,

Mumbai 400 001.

E-mail: MAKcustomercare2@bharatpetroleum.in

Tel No.: 022-24176151